



ATTORNEY'S DOCKET HIR-115
PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the application of:) Group Art Unit: 1773
)
KARAIWA) Examiner: JACKSON, M. R.
)
Serial No. 09/649,092)
)
Filed: August 28, 2000)

For: **THERMOPLASTIC ELASTOMER LAMINATED MATERIAL**

APPENDIX A

Please amend the following claims as indicated in the following marked-up copy of the claims.

1. (Once Amended) A laminated material
[characterized in that, in the laminated material wherein a polyolefinic thermoplastic elastomer (B) containing an oily softening agent is laminated on the surface layer]
comprising:

- (i) a surface layer comprising a polyolefinic thermoplastic elastomer (A) containing an oily softening agent, and
- (ii) an underlayer comprising a polyolefinic thermoplastic elastomer (B) containing an oily softening agent which underlayer is laminated on the surface layer,

wherein the ratio (a) of the oily softening agent to [the] amorphous component, [(]or if the polyethylene is incorporated, to the total of [the] an amorphous component and polyethylene [if polyethylene is incorporated)] in said thermoplastic elastomer (A) and the ratio (b) of the oily softening agent to [the] an amorphous component, [(]or if the polyethylene is incorporated, to the total of [the] an amorphous component and polyethylene [if polyethylene is incorporated)] in said thermoplastic elastomer (B) satisfy the following requisites;

ratio(a) \geq 0.8 X ratio (b),

ratio(a) = 5 to [200] 62.5 wt.%, and

ratio(b) = 5 to [200] 62.5 wt.%.

2. (Once Amended) A laminated material [characterized in that, in the laminated material] according to Claim 1, wherein the polyolefinic thermoplastic elastomer (A) and/or the polyolefinic thermoplastic elastomer (B) contain(s) polyethylene and in addition the ratio(a') of the oily softening agent to the amorphous component in said thermoplastic elastomer (A) and the ratio(b') of the oily softening agent to the amorphous component in said thermoplastic elastomer (B) satisfy the following requisites;

$\text{ratio}(a') \geq 0.8 \times \text{ratio}(b'),$

$\text{ratio}(a') = 5 \text{ to } [200] \text{ 62.5 wt.}, \text{ and}$

$\text{ratio}(b') = 5 \text{ to } [200] \text{ 62.5 wt.}.$



ATTORNEY'S DOCKET HIR-115
PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the application of:) Group Art Unit: 1773
KARAIWA) Examiner: JACKSON, M. R.
Serial No. 09/649,092)
Filed: August 28, 2000)

For: **THERMOPLASTIC ELASTOMER LAMINATED MATERIAL**

APPENDIX B

Please amend the following claims as indicated in the
following clean copy of the claims.

- Sub B1*
1. (Once Amended) A laminated material comprising:
- (i) a surface layer comprising a polyolefinic thermoplastic elastomer (A) containing an oily softening agent, and
 - (ii) an underlayer comprising a polyolefinic thermoplastic elastomer (B) containing an oily softening agent which underlayer is laminated on the surface layer,
- wherein the ratio (a) of the oily softening agent to amorphous component, or if the polyethylene is incorporated, to the total of an amorphous component and polyethylene in said thermoplastic elastomer (A) and the ratio (b) of the oily softening agent to an amorphous
- PH*

component, or if the polyethylene is incorporated, to the total of an amorphous component and polyethylene in said thermoplastic elastomer (B) satisfy the following requisites;

ratio(a) \geq 0.8 X ratio (b),

ratio(a) = 5 to 62.5 wt.%, and

ratio(b) = 5 to 62.5 wt.%.

2. (Once Amended) A laminated material according to

Claim 1,

wherein the polyolefinic thermoplastic elastomer (A) and/or the polyolefinic thermoplastic elastomer (B) contain(s) polyethylene and in addition the ratio(a') of the oily softening agent to the amorphous component in said thermoplastic elastomer (A) and the ratio(b') of the oily softening agent to the amorphous component in said thermoplastic elastomer (B) satisfy the following requisites;

ratio(a') \geq 0.8 X ratio (b'),

ratio(a') = 5 to 62.5 wt.%, and

ratio(b') = 5 to 62.5 wt.%.